




KÖSTER Restoration Plaster White/Fast

Technical Data Sheet M 663 030

Issued: 2018-07-23

- Test report according to DIN EN 998-1, MPA BAU Hannover

Fast setting, white, salt- and moisture resistant restoration plaster for inside and outside use

	KÖSTER BAUCHEMIE AG Dieselstraße 1-10, 26607 Aurich 13 M 663 EN 998-1:2010 Restoration Plaster (R) EN 998-1:2010 ZA.1
	Compressive strength 28 d CS II Capillary water uptake > 0.3 kg/m ² nach 24 Std Tensile strength 0.41 N/mm ² failure type B Dry density 1.45 kg/dm ³ Depth of water penetration ≤ 5 mm Coefficient of water vapor permeability μ 15 Reaction to fire A1

Features

KÖSTER Restoration Plaster White/Fast is a fast setting, salt and pressure resistant restoration plaster for the restoration of heavily moisture and salt burdened substrates. Due to its high porosity and hydrophobicity, KÖSTER Restoration Plaster White/Fast allows for the damage free drying and de-salting of masonry even in the case of high salt contents. It improves the insulative properties of the wall and therefore helps prevent the formation of condensate. KÖSTER Restoration Plaster White/Fast is free of light fillers and therefore requires no further surface treatment prior to the application of breathable paints or wallpaper which is open to vapor diffusion.

Technical Data

Porosity of fresh mortar	> 28 V-%
Porosity of cured plaster	> 40 V-%
Compressive strength (28 days)	> 8 N / mm ²
Flexural tensile strength (28 days)	> 3 N / mm ²
E-Modul	> 7000 N/mm ²
Setting time	approx. 30 minutes
Water consumption per 30 kg bag	4.0 - 4.2 l

Fields of Application

KÖSTER Restoration Plaster White/Fast is suitable for the repair of moisture and salt damaged masonry, also after the post installation of a horizontal barrier with KÖSTER Crisin 76 Concentrate, KÖSTER Mautrol, KÖSTER Mautrol 2C, or KÖSTER Mautrol Flex 2C. Especially for use in the KÖSTER Fast Restoration System which is comprised of KÖSTER Mautrol Flex 2C, KÖSTER NB 1 Fast and KÖSTER Restoration Plaster White/Fast. It is mainly used for small area waterproofing and restoration projects where a fast succession of work steps is necessary. It can be applied to reduce the formation of condensate after waterproofing rooms with high humidity using mineral sealing slurries such as the KÖSTER KD-System or KÖSTER NB 1 Grey. KÖSTER Restoration Plaster White/Fast can also be used as a decorative water repellent exterior plaster. In the case of exterior application we recommend the application of KÖSTER Repair Mortar on the base area up to 30 cm above ground level.

Substrate

Suitable substrates include concrete, masonry consisting of brick, natural stone, porous concrete block, perforated brick, mixed masonry, etc., sealing slurries such as KÖSTER NB 1 Grey, KÖSTER NB 2 White, or the KÖSTER KD-System. Prior to the application of KÖSTER Restoration Plaster White/Fast, the substrate is primed with KÖSTER Polysil TG 500 with a minimum consumption of 120 g / m². Apply the KÖSTER Polysil TG 500 until the surface is saturated. In the case of strongly absorbent substrates the consumption can be up to 250 g / m². Loose particles and salt efflorescence should be removed mechanically prior to the beginning of the restoration. Substrates containing gypsum are not suitable substrates and the gypsum must be removed.

Application

Directly after priming the substrate with KÖSTER Polysil TG 500 the key coarse is applied. The key coarse is made of KÖSTER Restoration Plaster White/Fast and KÖSTER SB Bonding Emulsion diluted in water on a ratio 1 : 3. The Key Coarse is cast onto the substrate with a brush or a trowel so that the plaster key is no thicker than 5 mm and covers approximately 50% of the area (Consumption approx. 3,5 - 4,0 kg / m²). Alternatively, the KÖSTER Restoration Plaster Key Coarse can be used (Consumption approx. 4 - 6 kg / m²). After hardening (approx. 30 to 60 minutes) the KÖSTER Restoration Plaster White/Fast can be applied.

Mix each 30 kg bag of KÖSTER Restoration Plaster White/Fast with 4.0 l to 4.2 l of clean potable water. Put 3.7 l of water in a clean mixing vessel and add the powder in portions while continually mixing using a slow speed mechanical compulsory mixer (under 400 rpm). Add in portions as much of the remaining water as necessary to achieve the desired consistency and mix until the mortar has a homogeneous texture. Mixing time is 3 minutes after all powder has been added to the liquid.

KÖSTER Restoration Plaster White/Fast is usually applied in two coats with a total layer thickness of approx. 2.5 cm; the thickness should be at least 2 cm. After casting the plaster onto the substrate, it is trued using a feather edge, a straight edge, or a long float trowel. Once the plaster starts to set it is smoothed using a float. Do not use a felt or sponge float to smooth the surface. Do not re-wet the surface after the initial floating. If several layers of plaster are to be applied, the lower layer is roughened thoroughly by scratching immediately after it begins to set.

Interior surfaces can be smoothed using KÖSTER Fine Plaster. KÖSTER Fine Plaster must be applied either within 48 hours after the application of the last coat of KÖSTER Restoration Plaster White/Fast or after the restoration plaster has cured for 28 days.

Aftertreatment

If aftertreatment is required or desired, for example due to very dry conditions, the plaster can be treated according to the general practice for mortars, such as covering with a thin PE sheet.

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu

Consumption

Approx. 12 kg / m² per cm layer thickness

On uneven surfaces additional consumption may have to be considered for levelling the surface.

Cleaning

Clean tools immediately after use with water.

Packaging

M 663 030 30 kg bag

Storage

Store the material in a dry environment. In originally sealed packages, the material can be stored for a minimum of 12 months.

Safety

Wear protective gloves and goggles when processing the material. Observe all governmental, state, and local safety regulations when processing the material.

Related products

KÖSTER Polysil TG 500	Prod. code M 111
KÖSTER Restoration Plaster Key Coarse	Prod. code M 154 025
KÖSTER Mautrol Liquid Sealant	Prod. code M 241
KÖSTER Crisin Cream	Prod. code M 278
KÖSTER Crisin 76 Concentrate	Prod. code M 279
KÖSTER Fine Plaster	Prod. code M 655 025
KÖSTER Façade Cream	Prod. code P 200
KÖSTER Silicone Paint White	Prod. code P 260 010
KÖSTER NB 1 Grey	Prod. code W 221 025
KÖSTER NB 2 White	Prod. code W 222 025
KÖSTER NB 1 Fast	Prod. code W 223 025
KÖSTER NB Elastic Grey	Prod. code W 233 033
KÖSTER NB Elastic White	Prod. code W 234 033
KÖSTER Repair Mortar	Prod. code W 530 025
KÖSTER SB Bonding Emulsion	Prod. code W 710
KÖSTER NB 1 Flex	Prod. code W 721 008

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction site and for the final results of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.